

Declaration: 3.3 Formaldehyde emissions: Supplier

to be completed by the wood-based panel supplier

I the undersigned, hereby declare that the _____ (insert product name and wood-based panel generic type, i.e. **particleboard, plywood, medium density fibreboard etc.**) meet the formaldehyde emission requirements of criterion 3.3 and provide test reports to support this declaration using one or more of the following standard approaches:

50% of E1:

Test value according to EN 717-1 = _____ (must be $\leq 0.062 \text{ mg/m}^3$)

Test value according to EN 717-2 = _____ (must be $\leq 1.75 \text{ mg/m}^2\text{h}$)*

*(can be $\leq 2.5 \text{ mg/m}^2\text{h}$ for plywood, solid wood panels or laminated veneer lumber if measured within 3 days of chamber test)

Test value according to EN 120 = _____ (must be $\leq 4 \text{ mg/100g}$ oven dry board)

CARB Phase II:

Test value according to ASTM E1333 = _____ (must be $\leq 0.05 \text{ ppm}$ for plywood, $\leq 0.09 \text{ ppm}$ for particleboard, $\leq 0.11 \text{ ppm}$ for medium density fibreboard or $\leq 0.13 \text{ ppm}$ for thin medium density fibreboard).

Test value according to ASTM D6007* = _____ *

Test value according to ASTM D5582* = _____ *

*results according to secondary ASTM methods (i.e. any method that is not ASTM E1333) should be accompanied by a declaration from the testing laboratory stating that the method used can be considered to produce results equivalent to ASTM E1333.

Japanese F star (3 or 4 star):

Test value according to JIS A 1460 = _____ (must be $\leq 0.5 \text{ mg/L}$ for 3 star or $\leq 0.3 \text{ mg/L}$ for 4 star)

Signature of person bearing legal responsibility	
Position held	
Company Name in CAPITALS:	
Date:	
Company Stamp:	

[Back to Declarations List](#)