

## Declaration: 6.1 Textile fabrics - Physical quality requirements

*to be completed by supplier of TEXTILE FABRIC upholstery covering materials*

*I the undersigned, hereby declare that the textile fabric upholstery covering material supplied to \_\_\_\_\_ (please insert the name of the applicant) meets the physical requirements as specified below and I attach copies of relevant test reports.*

- **Intended use of covering material:** \_\_\_\_\_ (choose from; "removable and washable" or "non-removable and washable").

- **Dimensional changes during washing and drying:** \_\_\_\_\_ (Not applicable to non-removable covering materials. According to ISO 6330 and EN ISO 5077 for domestic washing with 3 washing/drying cycles at specified temperature on product label or according to ISO 15797 and EN ISO 5077 for commercial washing at a minimum of 75°C. Results should be within  $\pm 2.0\%$  for woven fabrics,  $\pm 3.0\%$  for woven ticking fabrics,  $\pm 5.0\%$  for non-woven ticking fabrics or  $\pm 6.0\%$  for other non-woven fabrics).

- **Colour fastness to washing:** \_\_\_\_\_ (according to ISO 105-C06 for domestic washing or ISO 15797 and ISO 105-C06, at a minimum of 75°C, for commercial washing. Not applicable to non-removable covering materials. Results must be  $\geq$  level 3-4 for colour change and  $\geq$  level 3-4 for staining).

- **Colour fastness to wet rubbing:** \_\_\_\_\_ (Not applicable to white fabrics or fabrics that are neither dyed nor printed. Tests according to ISO 105 X12: Results must be  $\geq$  level 2-3 for removeable and non-removable covering materials).

- **Colour fastness to dry rubbing:** \_\_\_\_\_ (Not applicable to white fabrics or fabrics that are neither dyed nor printed. Tests according to ISO 105 X12: Results must be  $\geq$  level 4 for removable and non-removable covering materials).

- **Colour fastness to light:** \_\_\_\_\_ (According to ISO 105 B02: Results must be  $\geq$  level 5 for removeable and non-removable covering materials. The requirement can be reduced to  $\geq$  level 4 if the fabric is light coloured (i.e. standard depth  $< 1/12$ ) and consists of more than 20% wool/other keratin fibres or more than 20% linen/other bast fibres).

- **Fabric resistance to pilling:** \_\_\_\_\_ (According to ISO 12945-1 for knitted and non-woven fabrics or ISO 12945-2 for woven fabrics. Results must be  $> 3$  for both removable and non-removable covering materials).

- **Fabric resistance to abrasion (optional):** \_\_\_\_\_ (According to ISO 12947-2. Good results are indicated by a minimum of 50000 cycles using the Martindale method. Applicable to both removable and non-removable fabrics).

|   |  |
|---|--|
| <b>Signature of person bearing legal responsibility</b> |  |
| <b>Position held</b>                                    |  |
| <b>Company Name in CAPITALS:</b>                        |  |
| <b>Date:</b>  |  |
| <b>Company Stamp:</b>                                   |  |

[Back to Declarations List](#)